





FULL ARCHITECTURAL COLOR PALETTE



CORE COLORS

					
Regal White □ SR: .70 IE: .85 SRI: 85	Bone White □ SR: .68 IE: .86 SRI: 82	Stone White Δ SR: .62 IE: .85 SRI: 73	Almond Δ SR: .63 IE: .86 SRI: 75	Sandstone Δ SR: .47 IE: .86 SRI: 53	Sierra Tan SR: .30 IE: .85 SRI: 30
					
Medium Bronze SR: .26 IE: .84 SRI: 24	Mansard Brown SR: .29 IE: .86 SRI: 29	Dark Bronze SR: .26 IE: .84 SRI: 25	Extra Dark Bronze~ SR: .05 IE: .89 SRI: -1	Patina Green SR: .25 IE: .87 SRI: 24	Classic Green SR: .25 IE: .86 SRI: 24
					
Hartford Green~** SR: .10 IE: .86 SRI: 4	Teal** SR: .28 IE: .87 SRI: 28	True Black SR: .05 IE: .89 SRI: -1	Slate Blue SR: .27 IE: .86 SRI: 26	Regal Blue** SR: .30 IE: .86 SRI: 30	Terra Cotta SR: .39 IE: .85 SRI: 42
					
Banner Red** SR: .44 IE: .86 SRI: 49	Colonial Red SR: .31 IE: .87 SRI: 31	Brandywine** SR: .27 IE: .87 SRI: 27	Dove Gray SR: .49 IE: .87 SRI: 56	Slate Gray Δ SR: .37 IE: .86 SRI: 39	Charcoal SR: .08 IE: .90 SRI: 33
					
Matte Black SR: .26 IE: .86 SRI: 85	Silversmith Δ S15**.* SR: .48 IE: .80 SRI: 52	Champagne S20**.* SR: .37 IE: .83 SRI: 38	Pewter S11**.* SR: .36 IE: .85 SRI: 38	Bright Copper Δ S25**.* SR: .41 IE: .85 SRI: 44	Bright Silver Δ S66**.* SR: .55 IE: .77 SRI: 61
	*. Featuring a pearlescent mica finish; subject to premium pricing. Colors shown are as close to actual colors as allowed by the printing process. Actual metal samples are available. Colors may appear different when viewed at different angles and under different lighting conditions. Due to product improvements, changes and other factors, we reserve the right to change or delete information herein without prior notice. *. Acrylic Coated Galvalume also available (not pictured).				
Aged Copper Metallic**.* SR: .25 IE: .85 SRI: 23					

26G LOW GLOSS COLORS

					
Sierra Tan SR: .46 IE: .87 SRI: 52	Slate Gray SR: .37 IE: .86 SRI: 39	Medium Bronze SR: .31 IE: .87 SRI: 32	Dark Bronze SR: .28 IE: .86 SRI: 27	Colonial Red SR: .31 IE: .87 SRI: 31	Regal White □ SR: .70 IE: .85 SRI: 85
					
Dove Gray SR: .49 IE: .87 SRI: 56	Classic Green SR: .31 IE: .87 SRI: 32	Hartford Green** SR: .46 IE: .87 SRI: 32	Slate Blue SR: .30 IE: .87 SRI: 31	Matte Black SR: .26 IE: .86 SRI: 25	Mansard Brown SR: .29 IE: .86 SRI: 29
					
Bone White □ SR: .68 IE: .86 SRI: 82	Terra Cotta SR: .39 IE: .85 SRI: 42	Charcoal SR: .30 IE: .87 SRI: 31	Bright Silver** SR: .55 IE: .77 SRI: 61	Bright Copper** SR: .41 IE: .85 SRI: 44	

SR = Solar Reflectivity IE = Initial Emissivity SRI = Solar Reflective Index

** DENOTES EXOTIC COLORS AND ARE SUBJECT TO PREMIUM PRICING

Please check website for most up to date SR, IE, and SRI Values

□ LEED® compliant for low slope and steep slope

Δ LEED® compliant for steep slope only

PVDF - 70% polyvinylidene fluoride resin paint system

ARCHITECTURAL PVDF				STEEL				ALUMINUM			
COLOR	SR	IE	SRI	26GA. ¶	24GA. †	22GA. †‡	18GA. †‡	.032" †	.040" †	.050" †‡	.063" †‡
Regal White	.70	.85	85	LG ^	● ■	●	●	● ■	●	●	●
Bone White	.68	.86	82	LG ^	● ■	●	●	● ■	●	●	●
Stone White	.62	.85	73		● ■			● ■	●		
Almond	.63	.86	75		● ■			● ■	●	●	
Sandstone	.47	.86	53		● ■	●		● ■	●	●	
Sierra Tan	.30	.85	30	LG ^	● ■			● ■	●	●	●
Medium Bronze	.26	.84	24	LG ^	● ■	●	●	● ■	●	●	●
Mansard Brown	.29	.86	29	LG ^	● ■			● ■	●	●	
Dark Bronze	.28	.86	27	LG ^	● ■	●	●	● ■	●	●	●
Extra Dark Bronze	.05	.89	-1.0		● ■			● ■		●	
Patina Green	.25	.87	24		● ■			● ■	●		
Classic Green	.25	.86	24	LG ^	● ■	●		● ■	●		
Hartford Green **	.08	.09	4.0	LG	● ■			● ■		●	
Teal **	.28	.87	28		●						
Slate Blue	.26	.86	25	LG ^	● ■			● ■	●		
Regal Blue **	.28	.87	28		● ■			● ■	●		
Terra Cotta	.39	.85	42	LG ^	● ■			● ■			
Banner Red **	.44	.86	49		● ■			● ■			
Colonial Red	.31	.87	31	LG	● ■			● ■			
Brandywine**	.27	.87	27		● ■			● ■			
Dove Gray	.49	.87	56	LG ^	● ■			● ■			
Slate Gray	.37	.86	39	LG ^	● ■			● ■	●	●	
Charcoal	.32	.86	33	LG ^	● ■	●		● ■	●	●	●
Matte Black	.26	.86	25	LG ^	● ■	●		● ■	●	●	●
True Black	.05	.89	-1		● ■						
Bright Silver++	.55	.77	61	^	● ■			● ■	●	●	
Silversmith++	.48	.80	52		● ■			● ■			
Champagne++	.37	.83	38		● ■			● ■			
Pewter ++	.36	.85	38		● ■			● ■			
Bright Copper ++	.41	.85	44	^	● ■			● ■			
Aged Copper Metallic ++	.25	.85	23		● ■			● ■			

PAINT PERFORMANCE PROPERTIES	HOT DIPPED GALVANIZED STEEL OR GALVALUME®	ALUMINUM
Accelerated Weathering ASTM D 4587 (Drew Cycle Weatherometer) ASTM G-154 Chalk Rating Per ASTM D 4214, Method A	Hours: 3,000 Total Chalk: Rating 8 Color: 5 Δ E Hunter units max Hours: 5,000 Total Chalk: Rating 6 Color: 5 Δ E Hunter units max	Hours: 3,000 Total Chalk: Rating 8 Color: 5 Δ E Hunter units max Hours: 5,000 Total Chalk: Rating 6 Color: 5 Δ E Hunter units max
Salt Spray ASTM B 117	Hours: 1,000 Total Scribe: Rating ⅛" (2mm) Field: Rating 10, no blisters	Hours: 3,000 Total Scribe: Rating 10, no creepage Field: Rating 10, no blisters
Humidity ASTM D 2247	Hours: 2,000 Total Rating: 10, no blisters per ASTM D 714	Hours: 3,000 Total Rating: 10, no blisters per ASTM D 714
Formability ASTM D 4145	OT- 2T	OT- 2T
ASTM D 522 (Elongation over ⅛" mandrel)	No cracking No loss of adhesion	No cracking No loss of adhesion
Pencil Hardness ASTM D 3363	HB-2H	HB-2H
Abrasion Resistance ASTM D 968	55-75 Liters of falling sand	55-75 Liters of falling sand
Specular Gloss ASTM D 523	30 +/- 5 at 60° 55 +/- 5 at 85°	30 +/- 5 at 60° 55 +/- 5 at 85°
Reverse Impact ASTM D 2794	2 x Metal thickness in inch-lbs. No loss of adhesion. No cracking.	½ x Metal thickness in inch-lbs. No loss of adhesion. No cracking.
Flame Test ASTM E 84	Class A rated coating	Class A rated coating

† Standard Coil Width is 48.25"

‡ Standard Coil Width is 22 GA 48.25" 18 GA 44.375"

● Standard Color Option.

■ 40.5" Coil Option is Available.

▲ Additional Lead Times May Apply.

¶ Standard Coil Width 40.5"

LG Refers to Reflective Ratings

^ Offered in 27-1/2" coil width

++ Denotes Mica Colors

** Denotes exotic colors and are subject to premium pricing

NOTES ON AVAILABILITY:

- 24ga, .032, .040, .050, .063 are standard 48.25" in width. 22g 48.25" and 18ga 44.375" in width. 26ga is 40.5" standard width for painted items.
- Protective stippable film is standard on flat sheets.
- Mica++and exotics ** are subject to premium pricing. Due to the unique effect of the Mica finishes, appearances may vary from batch to batch.
- Standard inventory is non-embossed. Embossed requests are to be quoted.
- Unpainted, acrylic coated, aluminum-zinc alloy steel (AZ55) is maintained in 26ga 20", 26ga 27-1/2", 26ga 24", 24ga 20", 24ga 27-1/2", 24ga 24" slit coils and 26ga 48"x120", 24ga 48"x120" flat sheets (no strippable film).
- All colors are supplied in Medium Gloss (20-35 at 60 deg). Low gloss on non 26ga available subject to minimum coating run.
- This color chart is subject to change without notice.

SHERWIN-WILLIAMS.
Coil Coatings

Sherwin-Williams® is a trademark of SWIMC LLC.

